

ChemLINE[®] 784/32

A coating with superior chemical resistance and high temperature resistance.



Description

ChemLine[®] 784/32 is a high functionality, two component thermoset polymer coating. When cured, the ChemLine[®] 784/32 high cross-link density is unlike other coatings. ChemLine[®] 784/32 delivers significantly improved product performance and anti-corrosion resistance. ChemLine[®] 784/32 coating is formulated with a unique polymer designed and engineered with high functionality. This bridged aromatic backbone structure, when polymerized, forms up to 784 crosslinks. ChemLine[®] 784/32 cross-links predominately through an ether (carbon-oxygen-carbon) linkage. This eliminates high concentrations of hydroxyl groups (found in epoxies) and precludes formation of ester groups (found in vinyl esters) which are subject to hydrolysis and acid attack. ChemLine[®] 784/32 can be ambient cured or low temperature forced air cured depending on substrate and service conditions.*

ChemLine[®] 784/32's Higher Cross-Link Density Means:

- ▶ Higher chemical resistance
- ▶ Higher toughness
- ▶ Higher heat resistance
- ▶ Higher resistance to abrasion

Provides Superior Chemical Resistance to:

- ▶ 98% Sulfuric Acid
- ▶ Methanol
- ▶ 37% Hydrochloric Acid
- ▶ Methylene Chloride
- ▶ 50% Sodium Hydroxide
- ▶ Acetic Acid
- ▶ Most acids, alkalis, and solvents

Industry Applications

- ▶ **Chemical Processing** - Tanks, vessels, hazardous waste, secondary containment, chemical plant floors, etc.
- ▶ **Paper & Pulp** - Digesters, black liquor tanks, bleaching, etc.
- ▶ **Mining** - Acid tanks, scrubbers, etc.
- ▶ **High Technology** - Clean rooms, floors, etc.
- ▶ **Power Generation** - FGD systems, ducts and stacks, etc.
- ▶ **Steel** - Pickling tanks, acid storage, acid waste neutralization,
- ▶ **Waste Water** - Tanks, clarifiers, flocculation basins, neutralization chambers, concrete containment, etc.

Product Highlights

- ▶ Superior corrosion resistance, exceptional toughness
- ▶ Superior bonding qualities
- ▶ Applied to pitted and/or corroded steel
- ▶ Maximum versatility; product cycling
- ▶ Ambient or low temperature forced air cure
- ▶ Very low VOC - 99 grams/L (0.80 lbs. per gallon)
- ▶ Virtually non-permeable, steam cleanable, & field repairable
- ▶ Resists hydroblasting
- ▶ Excellent UV resistance
- ▶ Complies with all FDA regulations
- ▶ ChemLine[®] is generally recognized as safe (GRAS) for food grade cargoes.
- ▶ High impact resistance
- ▶ Dry heat resistance to 400° F (204° C)


Typical Properties

- ▶ Stock Colors _____ Gray, Red
- ▶ V.O.C. Level/Gal. _____ 99 grams/L (0.80 lbs./gal.)
- ▶ Lead Content _____ Zero
- ▶ Chromate Content _____ Zero
- ▶ Pot Life _____ 30 minutes @ 75°F (24°C)
- ▶ Viscosity Reduction _____ Reduce with Toluene or Xylene
- ▶ Solids by Volume _____ 89.6%
- ▶ Recommended Film Thickness (dry) mils average
_____ Steel: 12 mils (300 microns)
_____ Concrete: 20 mils (500 microns)
- ▶ Shelf Life _____ 12 months


**For product recommendations and technical, application and heat curing information contact Advanced Polymer Coatings' customer service. Contact +01 440-937-6218.*

► The Technology; Epoxies, Vinylesters and ChemLine® 784/32 Form 3 Dimensional Screen-Like Structures when Cured


The Greater the Distance Between the Crosslinks, the Greater the Permeation Causing Chemical Attack and Absorption



The Following Diagrams Represent the Same Coating Cutaway (pictured left)




Epoxy
2 Functionality
Forms 4 Cross-links



ChemLine® 784
High Functionality
Forms up to 784 Cross-links,
the Highest Cross-link Density

Problems with Epoxies and Vinylesters

Vinylester's and Epoxy's Open Screen Structure



AGGRESSIVE CHEMICAL MOLECULES PENETRATE INTO AND THROUGH THE POLYMER GROUPS ATTACKING BOTH THE INNER POLYMER STRUCTURE AND THE SUBSTRATE.

ChemLine 784's Closed Screen Structure



AGGRESSIVE CHEMICAL MOLECULES CANNOT PENETRATE THE HIGH DENSITY SURFACE. INNER POLYMER STRUCTURE AND SUBSTRATE PROTECTED FROM CHEMICAL ATTACK.

ChemLINE® 784/32

- High functionality forming up to 784 crosslinks
- Majority of crosslinks are through Ether (C-O-C) bonds. Ether bonds are one of the strongest bonds in chemistry. Ether bonds give flexibility with chemical resistance.

Superior Corrosion Resistance Performance

This is Only A Reference Guide. This is an abbreviated listing of the more than 5,000 chemicals that have been tested. This information is intended to serve as a reference guide only. The end user is responsible for determining if ChemLine® is the appropriate coating for the specific application involved. Contact your ChemLine® Representative or the ChemLine® Customer Service Hotline +01 440-937-6218 for detailed specifications prior to any final coatings recommendation or application.

	ChemLine®	Phenolic Epoxy	Vinylester	Stainless Steel		ChemLine®	Phenolic Epoxy	Vinylester	Stainless Steel		ChemLine®	Phenolic Epoxy	Vinylester	Stainless Steel
Acetaldehyde	A	L	N	A	Flaked Stearic Acid	A	N	A	A	Norval Amine	A	N	N	A
Acetic Acid	A	N	N	A	Fluoraboric Acid*	A	N	—	N	Octanoic Acid	A	A	—	A
Acrolein Acid	A	N	—	A	Formaldehyde	A	A	A	A	Orthonitro Benzene	A	N	N	N
Acrylic Acid	A	N	N	A	Formamide	A	N	—	A	Oleum	A	N	N	A
Acrylonitrile, (35°C)	A	N	N	A	Formic Acid 10%	A	N	A	A	Olive Oil Fatty Acid	A	A	A	A
Ammonium Persulfate	A	A	A	L	Green Liquor	A	N	A	L	Palm Oil Fatty Acid	A	A	A	A
Azabenzene	A	N	N	A	Glycerol	A	N	N	A	Perchloroethylene	A	N	N	A
Benzene	A	A	N	A	Grape Juice	A	A	A	A	Perchloric Acid	A	N	N	N
Benzene Carboxylic Acid	A	A	N	A	Grapefruit Juice	A	A	A	A	Phenol	A	N	N	A
Benzoyl Chloride	A	N	N	N	Grease Oil	A	A	A	A	Phosphoric Acid	A	N	A	N
B-Methacrylic Acid	A	N	N	A	Heptanoic Acid	A	A	—	A	Phthalic Anhydride	A	N	A	A
Bichromate of Soda	A	N	A	A	Herring Oil	A	A	A	A	Piperzine	A	N	—	A
Bromine	A	N	N	A	Hexahydroaniline	A	N	—	A	Polyethylene Polyamines	A	N	—	A
Butanoic Acid	A	N	—	A	HMDA	A	N	—	A	Potassium Hydroxide	A	A	L	L
Butyric Aldehyde	A	N	A	A	Hydrazine	A	N	N	A	Potassium Permanganate	A	A	A	L
Calcium Hydroxide	A	A	A	A	Hydrobromic Acid	A	N	A	N	Propionic Acid	A	N	N	A
Calcium Hypochlorite	A	A	A	L	Hydrochloric Acid	A	N	A	N	Pyridine	A	N	N	A
Caustic Potash	A	N	N	A	10% Hydrofluoric Acid*	A	N	A	N	Rubber Extender Oils	A	A	A	A
Carbolic Acid	A	N	N	A	5-20% Hydrogen Chloride	A	N	—	N	Rum	A	A	A	A
Chlorine Water	A	N	A	N	10%-30% Hydrogen Sulfate	A	N	A	A	Sodium Carbonate	A	N	A	N
Chlorosulfonic Acid	A	N	N	N	Isobutanol	A	N	A	A	Sodium Dichromate	A	N	A	A
Chlorinated Acetone	A	N	N	L	Isobutyric Acid	A	N	—	A	Sodium Hydroxide	A	A	A	L
Chloroacetic Acid	A	N	N	L	Isopropyl Amine	A	N	A	A	Sodium Sulfide	A	A	N	N
Chromic Acid, 20%	A	N	A	N	Javelle Water	A	N	A	N	Stannic Chloride	A	A	A	N
Coal Tar Oil	A	N	A	A	Juices, Fruit	A	A	A	A	Stearic Acid	A	A	A	A
Coconut Fatty Acid	A	A	A	A	Lactic Acid	A	A	A	A	Spent Sulfuric Acid	A	N	N	A
Colamine	A	N	N	A	Lactonitrile	A	N	—	A	Sulfur	A	N	N	A
Cresol	A	N	—	A	Latex	A	A	A	A	Sulfuric Acid 1-70%	A	A	A	N
Dichloromethane	A	N	N	A	Liquified Ammonia	A	N	N	A	Sulfuric Acid 70-99%	A	N	N	L
Detergents	A	A	A	A	Liquid Pitch Oil	A	N	A	A	Sulphurous Acid	A	N	N	A
Diethyl Formamide	A	N	N	A	M-Phosphoric Acid**	A	N	A	L	Tall Oil	A	A	A	A
Diethylamine	A	N	N	A	Maleic Anhydride	A	N	A	A	Tallow Acid	A	A	N	A
Diethylene Chloride	A	N	N	L	MCA	A	N	—	A	Tar Acid	A	N	A	A
Diethyl Ether	A	N	N	A	Methacrylonitrile, (35°C)	A	N	N	A	Tetra Chloroacetic Acid	A	N	N	N
Dimethylamide Acetate	A	N	—	A	Methanamide	A	N	—	A	Tetra Hydrofurfuryl Alcohol	A	N	N	A
Disulphuric Acid	A	N	—	A	Methanol	A	N	N	A	Toluene Diamine	A	N	N	A
EDTA	A	N	A	A	MEK	A	L	N	A	Toluol	A	L	L	A
Ethanolamine	A	N	N	A	Methylene Chloride	A	N	N	N	Valeraldehyde	A	N	—	A
Ethonic Acid Anhydride	A	N	—	A	Monochloro Benzene	A	N	N	N	Vinegar	A	N	A	A
Ethyl Acrylate	A	A	N	A	Naphtalene	A	N	A	A	Vitriol Oil 65%	A	N	A	A
Fatty Acids	A	A	A	A	Nitric Acid 1-20%	A	N	A	A	Water, Acid	A	N	N	A
Fatty Acid, Palm	A	A	A	A	Nitro Benzene	A	A	N	A	Xylenol	A	N	N	A
Ferric Chloride	A	N	A	N	Nitrogen Fertilizers	A	A	—	A					

A = Good at ambient temperatures L = Limited Service N = Not recommended

* ChemLine® 2400 Series ** ChemLine® 784 Series

Corrosion resistance data for Phenolic Epoxy, Vinylester and Stainless Steel from published literature.

ChemLINE® 784/32

A History of Performance

For more than a decade ChemLine® coatings have withstood the tremendous stresses and extremes of chemical attack and abrasive wear. ChemLine® has been proven worldwide under the most arduous operating conditions, from resisting the most aggressive chemicals to handling hot pipelines in sub-freezing temperatures, with a history of success. Based on this experience, the development of

ChemLine® 784/32 represents a quantum leap in chemical resistant polymer coatings.

Add to Your Profits — Specify ChemLine® 784/32

For the full story on ChemLine®, contact APC or click onto our web site at www.adv-polymer.com for the most versatile, technologically advanced and cost effective protection available.



The furnishing of the information contained herein does not constitute a representation by Advanced Polymer Coatings (APC) that any product or process is free from patent infringement claims of any third party, nor does it constitute the grant of a license under any patent of APC or any third party. APC assumes no liability for any infringement which may arise out of the use of the product. APC warrants that its products meet the specifications which it set for them. APC DISCLAIMS ALL OTHER WARRANTIES and relating to the products and DISCLAIMS ALL WARRANTIES RELATING TO THEIR APPLICATION expressed or implied INCLUDING but not limited to warranties of MERCHANTABILITY AND FITNESS for particular purpose. Receipt of products from APC constitutes acceptance of the terms of the Warranty; contrary provisions of purchase orders notwithstanding. In

the event that APC finds that products delivered are off-specification, APC will at its sole discretion, either replace the products or refund the purchase price thereof. APC's choice of one of these remedies shall be Buyer's sole remedy. APC will under no circumstances be libeled upon for consequential damages except in so far as liability is mandated by law. APC will deliver products at agreed upon times in so far as it is reasonably able to do so, but APC shall not be liable for failure to deliver on time when the failure is beyond its reasonable control. For the most current version of this literature, visit www.adv-polymer.com
© 2013 1202



Advanced Polymer Coatings
Avon, Ohio 44011 U.S.A.
+01 440-937-6218 Phone
+01 440-937-5046 Fax
800-334-7193 Toll-Free in USA & Canada

Advanced Polymer Coatings is an...



ABS Certified Manufacturing Company
ISO 9001: 2008
Certificate No. 43217

www.adv-polymer.com