ChemLINE® 784 ES
Elevated Service

TECHNICAL DATA SHEET

**This Technical Data Sheet supersedes those previously issued.*

DESCRIPTION

ChemLINE® 784 ES (Elevated Service) is engineered for concentrated acids, aggressive chemicals, and elevated operating temperatures. It provides superior chemical resistance to 98% sulfuric acid, methanol, 37% hydrochloric acid, methylene chloride, 50% sodium hydroxide, acetic acid, and more. This two-coat system builds on ChemLINE® 784's chemical and corrosion resistance, using APC's highly cross-linked polymer technology to deliver long-term protection and maintain lining integrity under severe chemical and thermal conditions.

TECHNICAL DATA

Color	Red, Grey
Solids Content, %	84% by volume
Finish	Semi-Gloss
VOC's	As supplied Grey 141 g/l (1.18 lb/gal) | Red 143 g/l (1.19 lb/gal) Thinned to max level Grey / Red 190 g/l (1.59 lb/gal)
Pot Life	120 minutes at 75°F (24°C)



SUBSTRATE & SURFACE PREPARATION

General	All surfaces to be coated should be clean, dry, and free from all contamination. All oil, grease, and other contaminants must be removed according to SSPC-SP 1 Solvent Cleaning prior to high pressure fresh water washing.
Steel Substrate	All surfaces to be coated shall be abrasively blast cleaned to NACE No 2 / SSPC-SP 10 / ISO Sa 2½ with a 3-4 mil (75 to 100 micron) blast profile.
Stainless Steel	All surfaces to be coated shall be abrasively blast cleaned to SSPC-SP 17 with a 3-4 mil (75 to 100 micron) blast profile.

MIXING & THINNING

Mixing	Mechanically agitate Component A (resin) for 1-2 minutes. Slowly add Component B (catalyst) to the resin and mix thoroughly for 3-5 minutes using a high shear (SSPC recommended) mechanical mixer. The mixture must be homogeneous and uniform in consistency.	
Ratio	One gallon kit	Part A: 0.98 gallons (3.7 liters) | Part B: 0.02 gallons (0.08 liters)
	Five gallon kit	Part A: 4.89 gallons (18.5 liters) | Part B: 0.11 gallons (0.40 liters)
Thinning	(if needed) Reduce with 0-5% (by volume) Toluene or Xylene.	

APPLICATION GUIDELINES

Equipment Type	Coating should be applied via airless spray equipment, pump size 45:1 or greater. Recommended airless tip sizes .017 to .023 inch. 3/8" ID hose size, 1/4" ID hose whip. *Contact APC Technical Service for additional information	
Dry Film Thickness (Total system thickness)	Average: 12-14 mils DFT (300-350 microns) Minimum: 10 mils DFT (250 microns) Maximum: 18 mils DFT (450 microns)	
Theoretical Coverage	at 1 mil: 1331 ft^2 / gallon (25 microns) at 12 mils: 110 ft^2 / gallon (300 microns) at 14 mils: 95 ft^2 / gallon (350 microns) *Allow for loss in mixing and application	at 1 mil: 32.6 m^2 / liter (25 microns) at 12 mils: 2.6 m^2 / liter (300 microns) at 14 mils: 2.3 m^2 / liter (350 microns) *Allow for loss in mixing and application
Re-coat Times	59ºF (15ºC) = minimum 12 hours, maximum 3 days (72 hours) 77ºF (25ºC) = minimum 8 hours, maximum 2 days (48 hours) 86ºF (30ºC) = minimum 6 hours, maximum 2 days (48 hours)	
Holiday Testing	High voltage holiday detector set at 3,000 volts, prior to repairs. Touch ups tested at 100 volts / mil.	

APPLICATION CONDITIONS

Material	55ºF (13ºC) – 95ºF (35ºC)
Substrate	59ºF (15ºC) – 104ºF (40ºC)
Humidity	10% – 50%

CLEAN-UP & SAFETY

Clean-up	ChemLINE® 784 ES can be cleaned up Acetone (preferred) or MEK.
Safety	Consult SDS

PACKAGING, HANDLING & STORAGE

Shelf Life	12 months
Storage	72ºF – 90ºF (22ºC - 32ºC) | 0 - 100% RH Consult SDS or contact APC Technical Service for more info.

Information on TDS documents represent typical data for the mixed coating formulation (part A + part B) using 'as supplied' materials as of the date hereof. All information is correct to the best of our knowledge. Values should not be construed as specifications. Please contact Advanced Polymer Coatings' Technical Service Team if you have any questions related to this data sheet or application.

APC GENERAL WARRANTY STATEMENT

The information provided by Advanced Polymer Coatings, Inc. (APC) for the application or repair of APC coatings is based upon protective coating industry standards and knowledge gained through observation of professional applicators throughout the world that have successfully applied APC coatings. APC does not exercise any control over selection of the applicator that applies or repairs APC coatings. By providing information APC is not representing, directly or by implication, that an applicator that is provided with this information will achieve a result that will pass without objection in the trade or industry, otherwise making any further warranty referred to as MERCHANTABILITY, or will meet the vessel owner's protective coating requirements, otherwise referred to as FITNESS FOR A PARTICULAR PURPOSE. The only warranty provided by APC through its information and literature is that all APC products when delivered will have been manufactured in accordance with APC's manufacturing procedures, will be accurately labeled, and when mixed, applied and cured in a controlled environment in accordance with APC's current written application guidelines will withstand chemical corrosion as set forth in APC's chemical compatibility reference guide. The chemical compatibility reference guide and current application guidelines are available at www.adv-polymer.com. Any customer specific express warranty can only arise from a written warranty extended by APC to the specific customer identified in the writing. APC DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE THAT ARE CONTAINED IN ARTICLE 2 OF THE UNITED STATES UNIFORM COMMERCIAL CODE AND ANY SIMILAR WARRANTIES CONTAINED IN THE LAWS OF OTHER COUNTRIES WHERE APC PRODUCTS ARE DELIVERED OR APPLIED. ALL CONTRACTS FOR THE SALE OF APC PRODUCTS SHALL BE GOVERNED BY THE UNIFORM COMMERCIAL CODE WITHOUT REGARD TO ANY STATE VARIATIONS.

ADVANCED POLYMER COATINGS